

Comment on "Photonic Band Gaps: Noncommuting Limits and the 'Acoustic Band'"

This Comment concerns the low-frequency dielectric constant ϵ_{eff} of 2D photonic crystals (PC's), constituted of circular cylinders (in vacuum) characterized by an *extremely high or infinite value of the dielectric constant*. In Ref. [1] and in two related papers [2,3] it was claimed that the quasistatic approach, based on the determination of the slope of the "acoustic" photonic band, leads to a value of ϵ_{eff} that is substantially smaller than the ϵ_{eff} obtained by an electrostatic method of "homogenization". Here we point out that this conclusion is incompatible with Electrodynamics and demonstrate that the two approaches do give the same results, essentially (within computational error).

Recently we have reported general formulas for the principal dielectric constants of an arbitrary 2D PC [4]. These formulas are obtained by taking the limit $\omega, k \rightarrow 0$ directly in the wave equation for periodic media. For isotropy in the plane of periodicity $A_{xy} = 0$ and $A_{xx} = A_{yy}$, so that $\epsilon_1 = \epsilon_2 \equiv \epsilon_{eff}$. Also, for $\epsilon \rightarrow \infty$, $\bar{\eta} = 1 - f$ and $\eta(\mathbf{G}) = -2fJ_1(Ga)/Ga$, where f is the filling fraction of the cylinders (radius a), J_1 is a Bessel function, and $\mathbf{G}$ is the reciprocal lattice vector. Then, for any isotropic 2D lattice, it follows from Ref. [4] that

$$\epsilon_{eff} = 1 / \left\{ 1 - f + f \sum_{\mathbf{G}, \mathbf{G}' \neq 0} \mathbf{G} \cdot \mathbf{G}' \frac{J_1(Ga)}{Ga} \frac{J_1(G'a)}{G'a} \times \left[\mathbf{G} \cdot \mathbf{G}' \frac{J_1(|\mathbf{G} - \mathbf{G}'|a)}{|\mathbf{G} - \mathbf{G}'|a} \right]^{-1} \right\}, \quad (1)$$

where the exponent -1 implies matrix inversion.

We have applied Eq. (1) to a square lattice; the last column of Table I gives the corresponding index of refraction $N_{eff} = \sqrt{\epsilon_{eff}}$. We see that there is excellent agreement with the static calculations [5], however poor accord with the results deduced from the slope of the acoustic band [1,2]. The authors of Ref. [1] attribute the discrepancy between the 2nd and 3rd columns to noncommuting limits $\epsilon \rightarrow \infty$ and $k \rightarrow 0$ (k is the Bloch vector). However, in our approach, these limits *do commute*, i.e. Eq. (1) and the results in the 4th column of the Table I are *independent on the order of taking the limits*. Precisely the commutation of these two limits

TABLE I. Effective indices of refraction N_{eff} for three values of the filling fraction f .

f	quasistatic approach, Refs. [1,2]	static approach, Ref. [5]	quasistatic approach, this Comment
0.363	1.1736	1.4663	1.4661
0.454	1.2151	1.6435	1.6443
0.554	1.2782	1.9135	1.9129

provides the possibility to obtain the solution of an electrostatic problem for conductors from the solution for dielectrics bodies of the same shape by taking the limit $\epsilon \rightarrow \infty$ [6]. We believe that the quasistatic results of Ref. [1–3] are erroneous for very large and for infinite values of ϵ , and that the reason for this resides in the truncation of the generalized Rayleigh identity to finite values of the order l ($l \leq 20$). If this truncation is performed *prior to taking the limit* $\epsilon \rightarrow \infty$, the stability of the numerical results does *not* guarantee that they are correct. (Indeed in Eq. (1) the truncation of the $\mathbf{G}$ values is the last step). We expect that for $\epsilon = 10^{10}$ [1], l_{max} should be extremely large and that for $\epsilon = \infty$ also $l_{max} \rightarrow \infty$. This is based on the fact that, the higher the dielectric contrast between the constituents, the greater the computational effort required. On the other hand, in Ref. [4] the contrast is given in terms of the *reciprocal* dielectric constants, leading to excellent convergence.

The physical explanation of the disagreement [1–3] has been attributed to the extremely small wavelength within the cylinders. However, this argument is invalid, because the homogenization (in periodic systems) implies averaging over scales much larger than the *Bloch wavelength* $2\pi/k$. Local wavelength in the material is meaningless. The reassuring conclusion is that Electrostatics is still the $\omega \rightarrow 0$ limit of Electrodynamics - even for PC's composed of cylinders with an infinite dielectric constant.

P.Halevi¹, A.A. Krokhin², and J. Arriaga²

¹Instituto Nacional de Astrofísica, Óptica y Electrónica, Apdo. Post. 51, Puebla, 72000, México

²Instituto de Física, Universidad Autónoma de Puebla, Apdo. Post. J-48, Puebla, 72570, México

Received 21 September 1999

PACS numbers: 42.70.Qs, 41.20.Jb, 41.20.Cv

-
- [1] N.A. Nicorovich, R.C. McPhedran, and L.C. Botten, Phys. Rev. Lett. **75**, 1507 (1995).
 - [2] N.A. Nicorovich, R.C. McPhedran, and L.C. Botten, Phys. Rev. E **52**, 1135 (1995).
 - [3] R.C. McPhedran, N.A. Nicorovich, and L.C. Botten, J. Electromagnetic Waves and Appl. **11**, 981 (1997).
 - [4] P. Halevi, A.A. Krokhin, and J. Arriaga, Phys. Rev. Lett. **82**, 719 (1999).
 - [5] W.T. Perrins, D.R. McKenzie, and R.C. McPhedran, Proc. Roy. Soc. Lond. **A 369**, 207 (1979).
 - [6] L.D. Landau, E.M. Lifshitz, and L.P. Pitaevskii, *Electrodynamics of Continuous Media*, 2nd ed., §§1 and 7 (Pergamon, Oxford, 1984).